

(19)

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11)

**EP 1 244 531 B1**

(12)

**EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention  
of the grant of the patent:  
06.10.2004 Bulletin 2004/41

(21) Application number: 00982580.3

(22) Date of filing: 11.12.2000

(51) Int Cl.7: **B22F 1/00**, B22F 3/00,  
B22F 7/00, B22F 7/04,  
B32B 5/16, B32B 9/00,  
B22F 7/06, B23P 15/28

(86) International application number:  
**PCT/US2000/033644**

(87) International publication number:  
**WO 2001/043899 (21.06.2001 Gazette 2001/25)**

**(54) COMPOSITE ROTARY TOOL AND TOOL FABRICATION METHOD**

KOMPOSIT-ROTATIONSWERKZEUG UND HERSTELLUNGSVERFAHREN DAFÜR  
OUTIL ROTATIF COMPOSITE ET SON PROCEDE DE FABRICATION

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE TR**

(30) Priority: 14.12.1999 US 460540

(43) Date of publication of application:  
02.10.2002 Bulletin 2002/40

(73) Proprietor: **TDY Industries, Inc.**  
Pittsburgh, PA 15222 (US)

(72) Inventors:  
• **MIRCHANDANI, Prakash, K.**  
Hampton Cove, AL 35763 (US)

• **KELLER, Bruce, A.**  
New Hope, AL 35760 (US)

(74) Representative: **Baker, Colin John**  
Eric Potter Clarkson  
Park View House  
58 The Ropewalk  
Nottingham NG1 5DD (GB)

(56) References cited:  
**EP-A- 0 453 428** **WO-A-98/28455**  
**US-A- 4 642 003** **US-A- 5 543 235**  
**US-A- 5 677 042** **US-A- 5 789 686**

**EP 1 244 531 B1**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

## Description

[0001] The present invention is generally directed to tools and tool blanks having a composite construction including regions of differing composition and/or microstructure. The present invention is more particularly directed to cemented carbide rotary tools and tool blanks for rotary tools having a composite construction. In addition, the present invention is directed to a method for producing rotary tools and rotary tool blanks having a composite construction. The method of the present invention finds general application in the production of rotary tools and may be applied in, for example, the production of cemented carbide rotary tools used in material removal operations such as drilling, reaming, countersinking, counterboring, and end milling.

## DESCRIPTION OF THE INVENTION BACKGROUND

[0002] Cemented carbide rotary tools (i.e., tools driven to rotate) are commonly employed in machining operations such as, for example, drilling, reaming, countersinking, counterboring, end milling, and tapping. Such tools are conventionally of a solid monolithic construction. The manufacturing process for such tools involves consolidating metallurgical powder (comprised of particulate ceramic and binder metal) to form a compact. The compact is then sintered to form a cylindrical tool blank having a solid monolithic construction. As used herein, monolithic construction means that the tools are composed of a material, such as, for example, a cemented carbide material, having substantially the same characteristics at any working volume within the tool. Subsequent to sintering, the tool blank is appropriately machined to form the cutting edge and other features of the particular geometry of the rotary tool. Rotary tools include, for example, drills, end mills, reamers, and taps.

[0003] Rotary tools composed of cemented carbides are adapted to many industrial applications, including the cutting and shaping of materials of construction such as metals, wood, and plastics. Cemented carbide tools are industrially important because of the combination of tensile strength, wear resistance, and toughness that is characteristic of these materials. Cemented carbides materials comprise at least two phases: at least one hard ceramic component and a softer matrix of metallic binder. The hard ceramic component may be, for example, carbides of elements within groups IVB through VIB of the periodic table. A common example is tungsten carbide. The binder may be a metal or metal alloy, typically cobalt, nickel, iron or alloys of these metals. The binder "cements" the ceramic component within a matrix interconnected in three dimensions. Cemented carbides may be fabricated by consolidating a metallurgical powder blend of at least one powdered ceramic component and at least one powdered binder.

[0004] The physical and chemical properties of ce-

mented carbide materials depend in part on the individual components of the metallurgical powders used to produce the material. The properties of the cemented carbide materials are determined by, for example, the chemical composition of the ceramic component, the particle size of the ceramic component, the chemical composition of the binder, and the ratio of binder to ceramic component. By varying the components of the metallurgical powder, rotary tools such as drills and end mills can be produced with unique properties matched to specific applications.

[0005] The monolithic construction of rotary tools inherently limits their performance and range of application. As an example, Figure 1 depicts side and end views of a twist drill 10 having a typical design used for creating and finishing holes in construction materials such as wood, metals, and plastics. The twist drill 10 includes a chisel edge 11, which makes the initial cut into the workpiece. The cutting tip 14 of the drill 10 follows the chisel edge 11 and removes most of the material as the hole is being drilled. The outer periphery 16 of the cutting tip 14 finishes the hole. During the cutting process, cutting speeds vary significantly from the center of the drill to the drill's outer periphery. This phenomenon is shown in Figure 2, which graphically compares cutting speeds at an inner (D1), outer (D3), and intermediate (D2) diameter on the cutting tip of a typical twist drill. In Figure 2 (b), the outer diameter (D3) is 2.54 cm (1.00 inch) and diameters D1 and D2 are 0.64 and 1.27 cm (0.25 and 0.50 inch) respectively. Figure 2(a) shows the cutting speeds at the three different diameters when the twist drill operates at 200 revolutions per minute. As illustrated in Figures 2(a) and (b), the cutting speeds measured at various points on the cutting edges of rotary tools will increase with the distance from the axis of rotation of the tools.

[0006] Because of these variations in cutting speed, drills and other rotary tools having a monolithic construction will not experience uniform wear and/or chipping and cracking of the tool's cutting edges at different points ranging from the center to the outside edge of the tool's cutting surface. Also, in drilling casehardened materials, the chisel edge is typically used to penetrate the case, while the remainder of the drill body removes material from the casehardened material's softer core. Therefore, the chisel edge of conventional drills of monolithic construction used in that application will wear at a much faster rate than the remainder of the cutting edge, resulting in a relatively short service life for such drills. In both instances, because of the monolithic construction of conventional cemented carbide drills, frequent regrinding of the cutting edge is necessary, thus placing a significant limitation on the service life of the bit. Frequent regrinding and tool changes also result in excessive downtime for the machine tool that is being used.

[0007] Other rotary tool types of a monolithic construction suffer from similar deficiencies. For example,

specially designed drill bits often are used for performing multiple operations simultaneously. Examples of such drills include step drills and subland drills. Step drills are produced by grinding one or more steps on the diameter of the drill. Such drills are used for drilling holes of multiple diameters. Subland drills may be used to perform multiple operations such as drilling, countersinking, and/or counterboring. As with regular twist drills, the service life of step and subland drills of a conventional monolithic cemented carbide construction may be severely limited because of the vast differences in cutting speeds experienced at the drills' different diameters.

[0008] The limitations of monolithic rotary tools are also exemplified in end mills. In general, end milling is considered an inefficient metal removal technique because the end of the cutter is not supported, and the length-to-diameter ratio of end mills is usually large (usually greater than 2:1). This causes excessive bending of the end mill and places a severe limitation on the depths of cut and feed rates that can be employed.

[0009] In order to address the problems associated with rotary tools of a monolithic construction, attempts have been made to produce rotary tools having different properties at different locations. For example, cemented carbide drills having a decarburized surface are described in U.S. Patent Nos. 5,609,447 and 5,628,837. In the methods disclosed in those patents, carbide drills of a monolithic cemented carbide construction are heated to between 600-1100°C in a protective environment. This method of producing hardened drills has major limitations. First, the hardened surface layer of the drills is extremely thin and may wear away fairly quickly to expose the underlying softer cemented carbide material. Second, once the drills are redressed, the hardened surface layer is completely lost. Third, the decarburization step, an additional processing step, significantly increases the cost of the finished drill.

[0010] Thus, there exists a need for drills and other rotary tools that have different characteristics at different regions of the tool. As an example, a need exists for cemented carbide drills and other rotary tools that will experience substantially even wear regardless of the position on the tool face relative to the axis of rotation of the tool. As an additional example, a need exists for stiffer end mills wherein the increased stiffness is not achieved at the expense of tensile strength and toughness.

[0011] WO-A-9828455 discloses a cemented carbide drill/endmill blank consisting of a core and a surrounding tube. The difference in Co-content between the core and tube is 1-10 wt.% units and the cubic carbide content is 8-20 wt.% in the tube and 0.5-2 wt.% in the core.

[0012] EP-A-0453428 discloses a method of manufacturing a cemented carbide body for cutting tools, rock drilling tools or wear parts with complicated geometry characterized in that the body is sintered together from simpler parts to a body with desired complex geometry.

[0013] US Patent 5789686 discloses methods for

making, methods for using and articles comprising cermets, preferably cemented carbides and more preferably tungsten carbide, having at least two regions exhibiting at least one property that differs. Preferably the cermets further exhibit a portion that is binder rich and which gradually or smoothly transitions to at least a second region. The cermets are manufactured by juxtaposing and densifying at least two powder blends having different properties (i.e. differential carbide grain size, differential carbide chemistry, differential binder content, differential binder chemistry, or any combination of the preceding). Preferably a first region of the cermet comprises a first ceramic component and a prescribed binder content and a second region, juxtaposing or adjoining the first region of the cermet comprises a second ceramic component and a second binder content less than the prescribed binder content.

#### SUMMARY OF THE INVENTION

[0014] The invention provides a composite rotary tool in accordance with claim 1 of the appended claims.

[0015] The present invention addresses the above-described needs by providing a composite rotary tool including at least a first (core) region and a second (outer) region. The tool is fabricated from cemented carbide, the first region of the composite rotary tool comprising a first cemented carbide material that is autogenously bonded to a second region which comprises a second cemented carbide material. As used herein, an "autogenous" bond refers to a bond that develops between regions of cemented carbide or other material without the addition of filler metal or other fusing agents. The first cemented carbide material and the second cemented carbide material differ with respect to modulus of elasticity and may also differ with respect to at least one other characteristic. This other characteristic may be, for example, hardness, wear resistance, fracture toughness, tensile strength, corrosion resistance, coefficient of thermal expansion, and coefficient of thermal conductivity. The core and outer regions of cemented carbide material within the tool are coaxially disposed and may be coaxially disposed or otherwise arranged with other regions so as to advantageously position the regions to take advantage of their particular properties. Preferred embodiments of the composite rotary tool of the present invention include twist drills, end mills, step drills, subland drills, and taps of a composite cemented carbide construction as described herein.

[0016] Cemented carbide materials generally include a binder and at least one carbide of an element selected from, for example, the group IVB, group VB and group VIB elements. The cemented carbide materials used in the present invention preferably include 60 to 98 weight percent of carbide component. The binder of cemented carbide materials typically is a metal selected from the group consisting of cobalt, nickel, iron, or alloys of these metals. The cemented carbide materials used in the

present invention preferably include 2 to 40 weight percent of binder. (All weight percent ranges provided herein are inclusive of the stated upper and lower extremes unless otherwise noted.) The properties of the cemented carbide materials used in the present invention may be tailored for specific applications by varying one or any combination of the chemical composition of the ceramic component, the grain size of the ceramic component, the chemical composition of the binder, or the ratio of the binder content to the ceramic component content.

[0017] In the present invention, one or more of the ceramic component or binder chemical composition, the ceramic component grain size, and the ratio of binder content to ceramic component content differ between the at least two regions of cemented carbide material so as to advantageously select the relative properties of the two or more regions of cemented carbide material. As an example, the hardness and wear resistance of one region of a rotary tool constructed according to the invention may be enhanced relative to another cemented carbide region. In that way, the tool may be constructed so that the regions of the cutting edge experiencing relatively high cutting speeds will wear and chip at a rate similar to that of regions experiencing lower cutting speeds. Although the present invention is presented in terms of rotary tools having a finite number of regions of cemented carbide material, it will be understood that the present invention may be applied to provide rotary tools with any number of regions of cemented carbide material, each having selected properties.

[0018] The invention also includes a novel method of producing composite rotary tools of the present invention in accordance with claim 13 of the appended claims. The method includes placing a first metallurgical powder into a first region of a void within a mold. A second metallurgical powder is placed into a second region of the void of the mold. The mold may be segregated into the two (or more) regions by, for example, placing a physical partition in the void of the mold to separate the regions. The metallurgical powders may be chosen to provide, on consolidation, cemented carbide materials having the desired properties as described above. A portion of at least the first metallurgical powder and the second metallurgical powder are placed in contact within the mold. The mold is then isostatically compressed to consolidate the metallurgical powders to form a compact. The compact is subsequently sintered to further densify the compact and to form an autogenous bond between the regions. Preferably, the compact is over pressure sintered at a pressure of 2.07-13.79 N/mm<sup>2</sup> (300-2000 psi) and at a temperature of 1350-1500°C. Subsequently, material may be removed from the sintered compact to form flutes or otherwise form a cutting edge or other features of the rotary tool.

[0019] The reader will appreciate the foregoing details and advantages of the present invention, as well as others, upon consideration of the following detailed description of embodiments of the invention. The reader

also may comprehend such additional details and advantages of the present invention upon using the invention.

## 5 BRIEF DESCRIPTION OF THE DRAWINGS

[0020] The features and advantages of the present invention may be better understood by reference to the accompanying drawings in which:

Figures 1(a) and 1(b) are plan and on-end views, respectively, of a conventional twist drill;

Figure 2(a) is a graph indicating cutting speeds at the three diameters D1, D2, and D3 of a conventional twist drill indicated in Figure 2(b);

Figure 3(a)-(d) are cross-sectional views of novel blanks useful for producing composite rotary tools constructed according to the present invention, and wherein Figure 3(b) is a cross-sectional end view of the blank shown in perspective in Figure 3(a);

Figure 4 is a partial cut-away plan view of an embodiment of a step drill constructed according to the present invention;

Figure 5 is a partial cut-away plan view of an embodiment of a subland drill constructed according to the present invention;

Figure 6 is a representation of the dry-bag isostatic pressing apparatus used in Example 1 to produce a composite end mill within the present invention;

Figure 7 is a photomicrograph taken at a magnification of 2000X of a region of interface between first and second regions of cemented carbide material in an end mill of the present invention fabricated in Example 1;

Figure 8 is a photomicrograph taken at a magnification of 1600X of a region of interface between first and second regions of cemented carbide material in an article according to the present invention fabricated in Example 2; and

Figure 9 is a photomicrograph taken at a magnification of 1000X of a region of interface between first and second regions of cemented carbide material in a composite rod fabricated according to the present invention in Example 3.

## DESCRIPTION OF EMBODIMENTS OF THE INVENTION

[0021] The present invention provides for rotary cutting tools and cutting tool blanks having a composite construction rather than the monolithic construction of conventional rotary tools. As used herein, a rotary tool is a tool having at least one cutting edge that is driven to rotate and which is brought into contact with a workpiece to remove material from the workpiece. As used herein, a rotary tool having a "composite" construction refers to one having regions differing in chemical composition and/or microstructure. These differences result

in the regions differing with respect to modulus of elasticity and they may also differ with respect to at least one other characteristic. This other characteristic may be selected from, for example, hardness, tensile strength, wear resistance, fracture toughness, corrosion resistance, coefficient of thermal expansion, and coefficient of thermal conductivity. Composite rotary tools that may be constructed as provided in the present invention include drills and end mills, as well as other tools that may be used in, for example, drilling, reaming, countersinking, counterboring, end milling, and tapping of materials.

[0022] The present invention more specifically provides a composite rotary tool having at least one cutting edge, such as a helically oriented cutting edge, and including at least two regions of cemented carbide material that are bonded together autogenously and that differ with respect to modulus of elasticity and that may also differ with respect to at least one other characteristic. The differing characteristics may be provided by variation of at least one of the chemical composition and the microstructure among the two regions of cemented carbide material. The chemical composition of a region is a function of, for example, the chemical composition of the ceramic component and/or binder of the region and the carbide-to-binder ratio of the region. For example, one of the two autogenously bonded cemented carbide material regions of the rotary tool exhibits a greater modulus of elasticity than the other of the two regions. Additionally, one of the two autogenously bonded cemented carbide material regions of the rotary tool may exhibit greater wear resistance and/or enhanced hardness than the other of the two regions.

[0023] Aspects of the present invention may be described in relation to the tool blank 30, shown in Figures 3(a) and (b) in cross-sectional views through the blank's central axis and transverse to that axis, respectively. The tool blank 30 is a generally cylindrical sintered compact with two coaxially disposed cemented carbide regions. It will be apparent to one skilled in the art, however, that the following discussion of the present invention also may be adapted to the fabrication of composite rotary tools and tool blanks having more complex geometry and/or more than two regions. Thus, the following discussion is not intended to restrict the invention, but merely to illustrate embodiments of it.

[0024] Referring again to Figures 3(a) and (b), the cylindrical rotary tool blank 30 comprised of two differing cemented carbide layers, a core region 31 and an outer region 32. The core region 31 and the outer region 32 are both of a cemented carbide material including ceramic particles in a continuous matrix of binder. Preferably the cemented carbide materials in the core region 31 and in the outer region 32 include a ceramic component composed of carbides of one or more elements belonging to groups IVB through VIB of the periodic table. The ceramic component preferably comprises about 60 to about 98 weight percent of the total weight of the cemented carbide material in each region. The carbide

particles are embedded within a matrix of binder material that preferably constitutes about 2 to about 40 weight percent of the total material in each region. The binder preferably is one or more of Co, Ni, Fe, and alloys of these elements. The binder also may contain, for example, elements such as W, Cr, Ti, Ta, V, Mo, Nb, Zr, Hf, and C up to the solubility limits of these elements in the binder. Additionally, the binder may contain up to 5 weight percent of elements such as Cu, Mn, Ag, Al, and Ru. One skilled in the art will recognize that any or all of the constituents of the cemented carbide material may be introduced in elemental form, as compounds, and/or as master alloys.

[0025] Again referring to Figures 3(a) and (b), the core region 31 of the tool blank 30 is autogenously bonded to the outer region 32 at an interface 33. The interface 33 is shown in Figures 3(a) and (b) to be cylindrical, but it will be understood that the shapes of the interfaces of cemented carbide material regions of the composite rotary tools of the present invention are not limited to cylindrical configurations. The autogenous bond between the regions at the interface 33 may be formed by, for example, a matrix of binder that extends in three dimensions from the core region 31 to the outer region 32, or vice versa. The ratio of binder to ceramic component in the two regions may be the same or different and may be varied between the regions to affect the regions' relative characteristics. By way of example only, the ratio of binder to ceramic component in the adjacent regions of the composite tool blank 30 may differ by 1 to 10 weight percent. The characteristics of the cemented carbide materials in the different regions of the composite rotary tools of the present invention may be tailored to particular applications.

[0026] One skilled in the art, after having considered the description of present invention, will understand that the improved rotary tool of this invention could be constructed with several layers of different cemented carbide materials to produce a progression of the magnitude of one or more characteristics from a central region of the tool to its periphery. Thus, for example, a twist drill may be provided with multiple, coaxially disposed regions of cemented carbide material and wherein each such region has successively greater hardness and/or wear resistance than the adjacent, more centrally disposed region. Alternately, rotary tools of the present invention could be made with other composite configurations wherein differences in a particular characteristic occur at different regions of the tool. Examples of alternate configurations are shown in Figures 3(c) and 3(d).

[0027] Figure 3(c) represents an embodiment of the present invention that is particularly useful as a cylindrical blank from which drills used for drilling case hardened materials may be produced. For drilling case hardened materials, the drill tip is typically used to penetrate the case, while the body of the drill removes material from the softer core. In this embodiment, the first region 34 and the second region 35 are disposed at first and

second ends of the blank. The first end would become a tip end of the drill, and the second end would become the end that would be secured in the chuck of the machine tool. The first region 34 may be composed of a hard and wear resistant material such as, for example, a cemented carbide of tungsten carbide particles (0.3 to 1.5  $\mu\text{m}$  average grain size) in a cobalt alloy binder comprising approximately 6 to 15 weight percent of the material in the first region 34. The second region 35 may be composed of, for example, tungsten carbide particles (1.0 to 10  $\mu\text{m}$  average grain size) in a cobalt alloy binder comprising approximately 2 to 6 weight percent of the material in second region 35. The first region 34 is autogenously bonded to the second region 35. The second region 35 has an enhanced modulus of elasticity relative to the first region 34 so as to resist flexing when pressure is applied to the drill

[0028] The embodiment shown in Figure 3(d) combines features of the embodiments of Figures 3(a) and 3(c). The cutting tip 36 includes two regions of different grades of cemented carbide material, a core region 37 and an outer region 38. The core and outer regions 37 and 38 are coaxially disposed and autogenously bonded to a third region 39. Regions 37 and 38 may be compositionally similar to regions 31 and 32 of the embodiment of Figures 3(a) and (b) or may be of other grades of cemented carbides so that the outer region 38 has enhanced hardness and wear resistance relative to the core region 37.

[0029] A major advantage of the composite cemented carbide rotary tools of the present invention is the flexibility available to tailor properties of regions of the tools to suit different applications. For example, the thickness, geometry, and/or physical properties of the individual cemented carbide material regions of a particular composite blank of the present invention may be selected to suit the specific application of the rotary tool fabricated from the blank. Thus, for example, the stiffness of one or more cemented carbide regions of the rotary tool experiencing significant bending during use may be of a cemented carbide material having an enhanced modulus of elasticity; the hardness and/or wear resistance of one or more cemented carbide regions having cutting surfaces and that experience cutting speeds greater than other regions may be increased; and/or the corrosion resistance of regions of cemented carbide material subject to chemical contact during use may be enhanced.

[0030] Composite rotary tools of the present invention may be made by any suitable process known in the art, but preferably are made using a dry bag isostatic method as further described below. The dry bag process is particularly suitable because it allows the fabrication of composite rotary tools and tool blanks with many different configurations, examples of which have been provided in Figures 3(a)-(d). The configurations shown in Figures 3(c) and (d) would be extremely difficult, if not impossible, to produce using other powder consolida-

tion techniques such as die compaction, extrusion, and wet bag isostatic pressing.

[0031] By way of example only, additional embodiments of rotary tools of the present invention are shown in Figures 4 and 5. Figure 4 depicts a step drill 110 constructed according to the present invention. The drill 110 includes a cutting portion 112 including several helically oriented cutting edges 114. The drill 110 also includes a mounting portion 116 that is received by a chuck to mount the drill to a machine tool (not shown). The drill 110 is shown in partial cross-section to reveal three regions of cemented carbide materials that differ relative to one another with regard to at least one characteristic. A first region 118 is disposed at the cutting tip of the drill 110. The cemented carbide material from which region 118 is composed exhibits an enhanced wear resistance and hardness relative to a central region 120 forming the core of the drill 110. The core region is of a cemented carbide material that exhibits an enhanced modulus of elasticity relative to the remaining two regions. The enhanced modulus of elasticity reduces the tendency of the drill 110 to bend as it is forced into contact with a work piece. The drill also includes an outer region 122 that defines the several helically oriented cutting edges 114. The outer region surrounds and is coaxially disposed relative to the core region 120. The outer region 122 is composed of a cemented carbide material that exhibits enhanced hardness and wear resistance relative to both the core region 120 and the tip region 118. The cutting surfaces 114 that are defined by the outer region 122 experience faster cutting speeds than cutting regions proximate to the drill's central axis. Thus, the enhanced wear resistance and hardness of the outer region 122 may be selected so that uniformity of wear of the cutting surfaces is achieved.

[0032] By way of example only, Figure 5 illustrates a subland drill 210 constructed according to the present invention. As with Figure 4, Figure 5 depicts the subland drill 210 in partial cross-section through the drill's central axis to expose three regions of different cemented carbide materials. As is discussed above, the different regions of cemented carbide material may differ in one or more of, for example, the chemical composition of the carbide component or binder component, the grain size of the carbide component, or the ratio of carbide component to binder in the material. The subland drill 210 includes a cutting portion 212 including a plurality of helically oriented cutting edges 214. The drill 210 also includes a mounting portion 216. A core region 218 of the drill 210 is composed of a cemented carbide material having an enhanced modulus of elasticity relative to the remaining two regions drill 210 exposed in cross-section. As with step drill 110, the core region 218 of subland drill 210 inhibits bending of the drill 210 upon application of pressure during drilling operations. A tip region 220 is composed of a cemented carbide material having an enhanced wear resistance and hardness relative to the core region 218. The advantages discussed with re-

spect to drill 110 are thereby achieved. The embodiment of Figure 5, however, differs from the embodiment of Figure 4 in that the core region 218 extends to the terminus 224 of the drill 210 and is coaxially disposed and surrounded by the tip region 220. The coaxial relationship of the core and tip regions 218 and 220, respectively, inhibits bending of the drill 210 in that portion of the cutting tip 212 adjacent terminus 224.

[0033] The present invention also includes methods of producing the composite rotary tools of the present invention and composite blanks used to produce those tools. One such method includes placing a first metallurgical powder into a void of a first region of a mold. Preferably, the mold is a dry-bag rubber mold. A second metallurgical powder is placed into a second region of the void of the mold. Depending on the number of regions of different cemented carbide materials desired in the rotary tool, the mold may be partitioned into additional regions in which particular metallurgical powders are disposed. The mold may be segregated into regions by placing a physical partition in the void of the mold to define the several regions. The metallurgical powders are chosen to achieve the desired properties of the corresponding regions of the rotary tool as described above. A portion of at least the first region and the second region are brought into contact with each other, and the mold is then isostatically compressed to densify the metallurgical powders to form a compact of consolidated powders. The compact is then sintered to further densify the compact and to form an autogenous bond between the first and second, and, if present, other regions. The sintered compact provides a blank that may be machined to include a cutting edge and/or other physical features of the geometry of a particular rotary tool. Such features are known to those of ordinary skill in the art and are not specifically described herein.

[0034] Actual examples of application of the foregoing method to provide composite rotary tools according to the present invention follow.

#### EXAMPLE 1

[0035] The present example applies the method of the present invention to manufacture a novel composite cemented carbide end mill improving upon the performance of conventional end mills of a monolithic construction. As is known, conventional end milling is a relatively inefficient metal removal technique because the end of the tool is not supported, and the tool's length-to-diameter ratio is typically large. This can result in excessive bending of the end mill and, therefore, low depths of cut, feed rates, and cutting speeds are usually employed. A composite end mill constructed according to the present invention may include a relatively stiff inner core region with a high modulus of elasticity to resist bending, and a relatively strong and tough outer region suitable for end milling applications.

[0036] In the present example, the end mill was pro-

vided with two coaxially disposed regions. The inner core region exhibits a high modulus of elasticity and, therefore, Teledyne (Laverne, Tennessee) grade HCA cemented carbide material was chosen as the material from which the core region is composed. In general, a cemented carbide having a lower binder content will have a high elastic modulus. Teledyne grade HCA contains 5.5 weight percent cobalt binder, tungsten carbide as the ceramic component, a medium grain structure, a hardness of 92.4 HRA, and a modulus of elasticity of approximately  $91 \times 10^6$  psi (635 kN/mm<sup>2</sup>). Teledyne grade H-91 was chosen as the material for the outer region (working surface). In general, grades suitable for milling must possess tensile strength and toughness to withstand the forces encountered during interrupted cutting. Teledyne grade H-91 has been found to be particularly suitable in many milling applications. Grade H-91 contains 11.0 weight percent cobalt binder, tungsten carbide as the ceramic component, a medium grain structure, a hardness of 89.7 HRA, and a modulus of elasticity of approximately  $82 \times 10^6$  psi (575 kN/mm<sup>2</sup>).

[0037] The end mill of the present example was produced from metallurgical powders using a dry-bag isostatic pressing apparatus as schematically depicted in Figure 6. The construction and manner of operation of a dry-bag isostatic press is known to those of ordinary skill in the art and, therefore, are not described in detail herein. As shown in Figure 6, a cylindrical sleeve in the form of a thin walled stainless steel tube 61 was inserted into a dry-bag isostatic mold 62. The inner region 63 of the tube 61 was filled with the first metallurgical powder to form the inner core region of the end mill (grade HCA cemented carbide material). The region 64 exterior to the tube 61 was filled with the second metallurgical powder to form the outer region of the end mill (grade H-91 cemented carbide material). The tube 61 was then removed from the mold 62 so that the first metallurgical powder and the second metallurgical powder came into contact. The powders were pressed in the mold at a pressure of about 207 N/mm<sup>2</sup> (30,000 psi) to form an approximately 36 cm (14 inch) long composite compact of two different cemented carbide grades. The compact was then over-pressure sintered in a sinter-HIP vacuum furnace (manufactured by AVS, Inc., Ayer, Massachusetts) at 1400°C and a pressure of approximately 5.5 N/mm<sup>2</sup> (800 psi). In the process of over-pressure sintering, also known as sinter-HIP, the chamber containing the compact is first heated to sintering temperature and is then pressurized. Compared with conventional HIP, sinter-HIP utilizes lower pressures and higher temperatures, is more cost effective, and produces a more uniform microstructure, all without sacrificing the reliability of the resulting component. The construction and manner of operation of a sinter-HIP vacuum furnace are known to those of ordinary skill in the art and, therefore, are not described in detail herein. Subsequent to completion of the over pressure sintering, the densified compact was suitably machined to form the cutting edges

and other surface features of the end mill.

[0038] Figure 7 is a photomicrograph at a magnification of 2000X of a region of the rotary tool manufactured as described in this example in the vicinity of the interface 73 between the first region 71 of cemented carbide material (grade HCA) and the second region 72 of cemented carbide material (grade H-91). The autogenous bond at interface 73 can be seen in the photomicrograph as a transition between the first region 71, which has a high ratio of binder to ceramic component relative to the second region 72. The photomicrograph shows that the depicted interface region lacks voids and inclusions.

#### EXAMPLE 2

[0039] The present example applies the method of the present invention to manufacture a novel composite cemented carbide drill improving upon the performance of conventional drills of a monolithic construction. As shown in Figure 1, the initial cut into the workpiece is made by the drill's chisel edge at a relatively small diameter on the drill's cutting edge. Also, as shown in Figures 2(a) and (b), the cutting speed is much slower at smaller diameters on the cutting edge. The inner core of the drill is thus expected to remove the bulk of the material at slow speeds (rough cutting) while the outer diameters of the cutting edge perform the finish cutting. This can result in the excessive build-up of heat in the center of the drill, resulting in premature thermal cracking. In addition, the core region can be expected to chip and fracture at a faster rate compared with the outer region. In order to obtain uniform chipping and wear, it is thus advantageous to have slightly softer and tougher (and hence resistant to chipping and thermal cracking) core. Thus, a composite drill constructed according to the present invention may include a relatively soft and tough inner region and a relatively hard and wear resistant outer region.

[0040] In the present example, the drill includes two coaxially disposed regions. The inner core region exhibits high toughness and, therefore, Teledyne grade FR-15 cemented carbide material was chosen as the material of the core region. In general, a cemented carbide having a high binder content will have a high toughness and resistance to chipping and thermal cracking. Teledyne grade FR-15 has been found to be particularly suitable for rough drilling applications. Grade FR-15 contains 15 weight percent cobalt binder, a tungsten carbide ceramic component, a fine grain structure (average grain size approximately 0.8 micron), and a hardness of 90.2 HRA. Teledyne grade FR-10 was chosen as the material for the outer region. Grade FR-10 has been found particularly suitable in high speed drilling applications. It contains 10 weight percent cobalt binder, a tungsten carbide ceramic component, a fine grain structure (average grain size 0.8 micron), and a hardness of 91.9 HRA.

[0041] As in Example 1, the drill of Example 2 was

produced from metallurgical powders using a dry-bag isostatic pressing apparatus as schematically depicted in Figure 6. A partition in the form of a stainless steel tube 61 was inserted into dry-bag isostatic mold 62. The inner region of the tube 61 was filled with grade FR-15 powder to form the inner core region of the drill. The region 64 exterior to the tube 61 was filled with grade FR-10 powder to form the outer region of the drill. The tube 61 was then removed from the mold 62 so that the two powder grades came into contact. The powders were pressed at a pressure of about 207 N/mm<sup>2</sup> (30,000 psi) to form a composite compact approximately 36 cm (14 inches) long. The compact was then over pressure sintered as in Example 1, and subsequently machined to form the cutting edge and other surface features of drill.

[0042] Figure 8 is a photomicrograph at a magnification of 1600X of a region of the drill manufactured as described in this example in the vicinity of the interface 83 between the first region 81 of cemented carbide material (grade FR-15) and the second region 82 of cemented carbide material (grade FR-10). The autogenous bond at interface 83 can be seen in the photomicrograph as a transition between the first region 81, which has a high ratio of binder to ceramic component relative to the second region 82. The photomicrograph shown that the depicted interface region lacks voids and inclusions.

#### EXAMPLE 3

[0043] The rotary tools in Examples 1 and 2 included regions of cemented carbide grades differing in cobalt binder content. The tungsten carbide grain sizes in the regions, however, were approximately the same. In the present example, a rotary tool blank in the form of a composite rod was provided by combining cemented carbide grades differing in binder content and average tungsten carbide grain size. A first region of the composite rod was composed of Teledyne grade H-17, which has a fine carbide grain structure. (Grade H-17 has an average grain size of approximately 0.8 microns, a cobalt content of 10.0 weight percent, and a hardness of 91.7 HRA.) A second region of the composite rod was composed of Teledyne grade R-61, which has a coarse carbide grain structure. (Grade R-61 has an average grain size of approximately 4.0 microns, a cobalt content of 15.0 weight percent, and a hardness of 86.0 HRA.) The composite rod was fabricated by substantially the same methods as used in Examples 1 and 2.

[0044] Figure 9 is a photomicrograph at a magnification of 1000X of a region of the composite rod of this example in the vicinity of the interface 93 between the first region 91 (grade H-17) and the second region 92 (grade R-61). The autogenous bond at interface 93 can be seen in Figure 9 as a transition between the two regions. This example further illustrates the great flexibility available using the process of the present invention to



tailor the characteristics of different regions of the rotary tools of the invention to match specific applications.

[0045] Although the present invention has been described in connection with certain embodiments, those of ordinary skill in the art will, upon considering the foregoing description, recognize that many modifications and variations of the invention may be employed. All such variations and modifications of the present invention are intended to be covered by the foregoing description and the following claims.

#### Claims

1. A composite rotary tool (30,110,210) comprising:
  - an elongate portion including at least a coaxially disposed core region (31) and outer region (32), said elongate portion defining a helically oriented cutting edge (114,214) and said core region (31) being autogenously bonded to said outer region (32),
  - characterized in that:
    - said core region (31) comprises a first cemented carbide material having a modulus of elasticity from 630-665 kN/mm<sup>2</sup> (90x10<sup>6</sup> psi to 95x10<sup>6</sup> psi);
    - said outer region (32) comprises a second cemented carbide material having a modulus of elasticity from 483-644 kN/mm<sup>2</sup> (69x10<sup>6</sup> psi to 92x10<sup>6</sup> psi) and
    - said modulus of elasticity of the second cemented carbide material is selected to be different from and less than the modulus of elasticity of the first cemented carbide material.
2. The composite rotary tool (30,110,210) of claim 1, wherein said first cemented carbide material and said second cemented carbide material individually comprise a binder and a metal carbide.
3. The composite rotary tool (30,110,210) of claim 2, wherein said metal of said metal carbide of said first cemented carbide material and said metal of said metal carbide of second carbide material are individually selected from the group consisting of group IVB, group VB and group VIB elements.
4. The composite rotary tool (30,110,210) of claim 2, wherein said core region (31) is autogenously bonded to said outer region (32) by a matrix of said binder of at least one of said first cemented carbide material and said second carbide material.
5. The composite rotary tool (30,110,210) of claim 2, wherein said binder of said first cemented carbide material and said binder of said second cemented carbide material each individually comprise a metal selected from the group consisting of cobalt, cobalt alloy, nickel, nickel alloy, iron, and iron alloy.
6. The composite rotary tool (30,110,210) of claim 2, wherein said first cemented carbide material and said second cemented carbide material each comprises 2 to 40 weight percent of said binder and 60 to 98 weight percent of said metal carbide.
7. The composite rotary tool (30,110,210) of claim 1, wherein at least one of said first cemented carbide material and said second cemented carbide material comprise tungsten carbide particles having an average grain size of 0.3 to 10 µm.
8. The composite rotary tool (30,110,210) of claim 1, wherein one of said first cemented carbide material and said second cemented carbide material comprises tungsten carbide particles having an average grain size of 0.5 to 10 µm and the other of said first cemented carbide material and said second cemented carbide material comprises tungsten carbide particles having an average particle size of 0.3 to 1.5 µm.
9. The composite rotary tool (30,110,210) of claim 1, wherein the composite rotary tool (30,110,210) is selected from the group consisting of a drill, an end mill, and a tap.
10. The composite rotary tool (30,110,210) of claim 2, wherein one of said first cemented carbide material and said second carbide material includes 1 to 10 weight percent more of said binder than the other of said first cemented carbide material and said second cemented carbide material.
11. The composite rotary tool (30,110,210) of claim 1, wherein at least one of the hardness and wear resistance of said first cemented carbide material within said core region (31) differs from that of said second cemented carbide material within said outer region (32).
12. The composite rotary tool (30,110,210) of claim 1, wherein said first cemented carbide material comprises 2 to 6 weight percent cobalt alloy and said second cemented carbide material comprises 6 to 15 weight percent cobalt alloy.
13. A method of producing a composite rotary tool in accordance with any one of claims 1 to 12, the method comprising:

- placing a first metallurgical powder into a first region of a void of a mold;  
 placing a second metallurgical powder into a second region of the void, the first metallurgical powder differing from the second metallurgical powder, said first metallurgical powder being selected to provide, on consolidation, a first cemented carbide material having a modulus of elasticity from 630-665 kN/mm<sup>2</sup> (90x10<sup>6</sup> psi to 95x10<sup>6</sup> psi) and said second metallurgical powder being selected to provide, on consolidation, a second cemented carbide material having a modulus of elasticity from 483-644 kN/mm<sup>2</sup> (69x10<sup>6</sup> psi to 92x10<sup>6</sup> psi), said modulus of elasticity of the second cemented carbide material being selected to be different from and less than the modulus of elasticity of the first cemented carbide material.  
 contacting at least a portion of the first metallurgical powder with the second metallurgical powder;  
 compressing the mold to consolidate the first metallurgical powder and the second metallurgical powder to form a compact;  
 over-pressure sintering the compact; and  
 removing material from the compact to provide at least one helically oriented cutting edge.
14. The method of claim 13, wherein the mold is a dry-bag rubber mold, and further wherein compressing the mold comprises isostatically compressing the dry-bag rubber mold to form the compact.
15. The method of claim 13, wherein removing material from the compact comprises machining the compact to form at least one helically oriented flute defining at least one helically oriented cutting edge.
16. The method of claim 13, further comprising:  
 physically partitioning a void of the dry-bag isostatic rubber mold into at least the first region and the second region.
17. The method of claim 16, wherein physically partitioning the void comprises inserting a sleeve into the void to divide the first region and the second region.
18. The method of claim 17, wherein contacting at least a portion of the first metallurgical powder with the second metallurgical powder comprises removing the sleeve from the void after placing the first metallurgical powder and second metallurgical powder into the mold.
19. The method of claim 13, wherein over pressure sintering the compact comprises heating the compact

at a temperature of 1350°C to 1500°C under a pressure of 2.07-13.79 N/mm<sup>2</sup> (300-2000 psi).

20. The method of claim 13, wherein contacting at least a portion of the first metallurgical powder with the second metallurgical powder comprises placing one of the first metallurgical powder and the second metallurgical powder into the void so as to be in contact along an interface with the other of the first metallurgical powder and the second metallurgical powder.
21. The method of claim 13, wherein compressing the mold comprises isostatically compressing the mold at a pressure of 34.5-345 N/mm<sup>2</sup> (5,000 to 50,000 psi).

#### Patentansprüche

1. Verbund-Rotationswerkzeug (30,110,210) mit:

einem länglichen Abschnitt mit mindestens einem koaxial angeordneten Kernbereich (31) und einem Außenbereich (32), wobei der längliche Abschnitt ein spiralförmig ausgerichtete Schneidkante (114,214) festlegt und der Kernbereich (31) autogen an den Außenbereich (32) gebondet ist,

#### dadurch gekennzeichnet, dass

der Kernbereich (31) ein erstes Hartmetallmaterial (Zementkarbidmaterial) mit einem Elastizitätsmodul von 630-665 kN/mm<sup>2</sup> (90x10<sup>6</sup> psi bis 95x10<sup>6</sup> psi) aufweist,

der Außenbereich (32) ein zweites Hartmetallmaterial mit einem Elastizitätsmodul von 483-644 kN/mm<sup>2</sup> (69x10<sup>6</sup> psi bis 92x10<sup>6</sup> psi) aufweist, und das Elastizitätsmodul des zweiten Hartmetallmaterials so gewählt ist, dass es sich von dem Elastizitätsmodul des ersten Hartmetallmaterials unterscheidet und geringer ist.

2. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 1, wobei das erste Hartmetallmaterial und das zweite Hartmetallmaterial individuell jeweils ein Bindemittel und ein Metalkarbid umfassen.
3. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 2, wobei das Metall des Metalkarbids des ersten Hartmetallmaterials und das Metall des Metalkarbids des zweiten Hartmetallmaterials individuell aus der aus Elementen der Gruppe IVB, der Gruppe VB und der Gruppe VIB bestehenden Gruppe ausgewählt ist.
4. Verbund-Rotationswerkzeug (30,110,210) nach

Anspruch 2, wobei der Kernbereich (31) autogen an den Außenbereich (32) durch eine Matrix des Bindemittels aus dem ersten Hartmetallmaterial und/oder dem zweiten Hartmetallmaterial gebondet ist.

5. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 2, wobei das Bindemittel des ersten Hartmetallmaterials und das Bindemittel des zweiten Hartmetallmaterials jeweils individuell ein Metall aufweisen, das aus Kobalt, Kobaltlegierung, Nickel, Nickellegierung, Eisen und Eisenlegierung bestehenden Gruppe ausgewählt ist. 5
6. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 2, wobei das erste Hartmetallmaterial und das zweite Hartmetallmaterial jeweils 2 bis 40 Gewichtsprozent des Bindemittels und sechzig bis 98 Gewichtsprozent des Metallkarbids umfassen. 10
7. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 1, wobei das erste Hartmetallmaterial und/oder das zweite Hartmetallmaterial Wolframkarbidpartikel mit einer durchschnittlichen Korngröße von 0,3 bis 10µm aufweist. 15
8. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 1, wobei das erste Hartmetallmaterial oder das zweite Hartmetallmaterial Wolframkarbidpartikel mit einer durchschnittlichen Korngröße von 0,5 bis 10µm umfasst und das jeweils andere Hartmetallmaterial Wolframkarbidpartikel mit einer durchschnittlichen Partikelgröße von 0,3 bis 1,5µm umfasst. 20
9. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 1, wobei das Verbund-Rotationswerkzeug (30,110,210) aus der aus einem Bohrer, einem Endfräser und einem Gewindebohrer bestehenden Gruppe ausgewählt ist. 25
10. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 2, wobei das erste Hartmetallmaterial oder das zweite Hartmetallmaterial 1 bis 10 Gewichtsprozent mehr Bindemittel aufweist als das jeweils andere Hartmetallmaterial aufweist. 30
11. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 1, wobei die Härte und/oder die Verschleißfestigkeit des ersten Hartmetallmaterials innerhalb des Kernbereichs (31) sich von derjenigen des zweiten Hartmetallmaterials in dem Außenbereich (32) unterscheidet. 35
12. Verbund-Rotationswerkzeug (30,110,210) nach Anspruch 1, wobei das erste Hartmetallmaterial zwei bis sechs Gewichtsprozent Kobaltlegierung und das zweite Hartmetallmaterial 6 bis 15 Gewichtsprozent Kobaltlegierung aufweist. 40

13. Verfahren zur Herstellung eines Verbund-Rotationswerkzeugs gemäß einem der Ansprüche 1 bis 12, wobei das Verfahren umfasst:

Einbringen eines ersten Metallpulvers in einen ersten Bereich eines Hohlraums einer Form, Einbringen eines zweiten Metallpulvers in einen zweiten Bereich des Hohlraums, wobei sich das erste Metallpulver von dem zweiten Metallpulver unterscheidet und das erste Metallpulver so gewählt ist, dass es bei Verfestigung ein erstes Hartmetallmaterial (Zement-Karbidmaterial) mit einem Elastizitätsmodul von 630-665 kN/mm<sup>2</sup> (90x10<sup>6</sup> psi bis 95x10<sup>6</sup> psi) aufweist und das zweite Metallpulver so gewählt ist, dass es bei Verfestigung ein zweites Hartmetallmaterial (Zement-Karbidmaterial) mit einem Elastizitätsmodul von 483-644 kN/mm<sup>2</sup> (69x10<sup>6</sup> psi bis 92x10<sup>6</sup> psi) aufweist, wobei das Elastizitätsmodul des zweiten Hartmetallmaterials so gewählt ist, dass es sich von dem Elastizitätsmodul des ersten Hartmetallmaterials unterscheidet und geringer ist, In-Kontakt-Bringen mindestens eines Teils des ersten Metallpulvers mit dem zweiten Metallpulver, Unter-Druck-Setzen der Form, um das erste Metallpulver und das zweite Metallpulver zu verfestigen, um einen Kompaktkörper zu bilden, Überdruck-Sintern des Kompaktkörpers, und Entfernen von Material von dem Kompaktkörper, um mindestens eine spiralförmig ausgerichtete Schneidkante bereitzustellen.

14. Verfahren nach Anspruch 13, wobei die Form eine Trockentaschen-Gummiorm ist, und wobei ferner das Unter-Druck-Setzen der Form ein isostatisches Komprimieren der Trockentaschen-Gummiorm umfasst, um den Kompaktkörper zu bilden. 45

15. Verfahren nach Anspruch 13, wobei das Entfernen von Material von dem Kompaktkörper ein spanabhebendes Bearbeiten des Kompaktkörpers umfasst, um mindestens eine spiralförmig ausgerichtete Spannut zu bilden, die mindestens eine spiralförmig ausgerichtete Schneidkante festlegt. 50

16. Verfahren nach Anspruch 13, ferner umfassend:

physisches Unterteilen eines Hohlraums der isostatischen Trockentaschen-Gummiorm in mindestens den ersten Bereich und den zweiten Bereich.

17. Verfahren nach Anspruch 16, wobei das physische Unterteilen des Hohlraums das Einsetzen einer Hülse in den Hohlraum umfasst, um den ersten Be-

reich und den zweiten Bereich zu unterteilen.

18. Verfahren nach Anspruch 17, wobei das In-Kontakt-Bringen mindestens eines Teils des ersten Metallpulvers mit dem zweiten Metallpulver das Entfernen der Hülse aus dem Hohlraum umfasst, nachdem das erste Metallpulver und das zweite Metallpulver in die Form eingebracht wurden.

19. Verfahren nach Anspruch 13, wobei das Überdruck-Sintern des Kompaktkörpers ein Erhitzen des Kompaktkörpers auf eine Temperatur von 1350° Celsius bis 1500° Celsius bei einem Druck von 2,07 bis 13,79 N/mm<sup>2</sup> (300 bis 2000 psi) umfasst.

20. Verfahren nach Anspruch 13, wobei das In-Kontakt-Bringen mindestens eines Teils des ersten Metallpulvers mit dem zweiten Metallpulver ein Einbringen des ersten Metallpulvers oder des zweiten Metallpulvers in den Hohlraum umfasst, so dass es entlang einer Grenzfläche mit dem jeweils anderen Metallpulver in Kontakt kommt.

21. Verfahren nach Anspruch 13, wobei das Unter-Druck-Setzen der Form ein isostatisches Unter-Druck-Setzen der Form bei einem Druck von 34,5 bis 345 N/mm<sup>2</sup> (5.000 bis 50.000 psi) umfasst.

#### Revendications

1. Outil rotatif composite (30, 110, 210) comprenant :

une partie allongée comprenant au moins une âme (31) et une région extérieure (32) disposées coaxialement, ladite partie allongée définissant une arête tranchante orientée en hélice (114, 214) et l'âme (31) étant soudée de manière autogène à ladite région extérieure (32),

caractérisé en ce que :

l'âme (31) comprend un premier matériau en carbure cémenté présentant un module d'élasticité compris entre 630 et 665 kN/mm<sup>2</sup> (entre 90x10<sup>6</sup> psi et 95x10<sup>6</sup> psi), ladite région extérieure (32) comprend un second matériau en carbure cémenté présentant un module d'élasticité compris entre 483 et 644 kN/mm<sup>2</sup> (entre 69x10<sup>6</sup> psi et 92x10<sup>6</sup> psi) et ledit module d'élasticité du second matériau en carbure cémenté est sélectionné pour être différent du et inférieur au module d'élasticité du premier matériau en carbure cémenté.

2. Outil rotatif composite (30, 110, 210) selon la revendication 1, caractérisé en ce que ledit premier ma-

tériau en carbure cémenté et ledit second matériau en carbure cémenté comprennent individuellement un liant et un carbure métallique.

3. Outil rotatif composite (30, 110, 210) selon la revendication 2, caractérisé en ce que ledit métal dudit carbure métallique dudit premier matériau en carbure cémenté et ledit métal dudit carbure métallique dudit second matériau en carbure cémenté sont sélectionnés individuellement dans le groupe comprenant des éléments du groupe IVB, du groupe VB et du groupe VIB.

4. Outil rotatif composite (30, 110, 210) selon la revendication 2, caractérisé en ce que l'âme (31) est soudée de manière autogène à ladite région extérieure (32) par une matrice dudit liant d'au moins l'un dudit premier matériau en carbure cémenté et dudit second matériau en carbure cémenté.

5. Outil rotatif composite (30, 110, 210) selon la revendication 2, caractérisé en ce que ledit liant dudit premier matériau en carbure cémenté et ledit liant dudit second matériau en carbure cémenté comprennent chacun individuellement un métal sélectionné dans le groupe constitué de cobalt, d'alliage de cobalt, de nickel, d'alliage de nickel, de fer et d'alliage de fer.

6. Outil rotatif composite (30, 110, 210) selon la revendication 2, caractérisé en ce que ledit premier matériau en carbure cémenté et ledit second matériau en carbure cémenté comprennent chacun 2 à 40 pour cent en poids dudit liant et entre 60 et 98 pour cent en poids dudit carbure métallique.

7. Outil rotatif composite (30, 110, 210) selon la revendication 1, caractérisé en ce qu'au moins l'un dudit premier matériau en carbure cémenté et dudit second matériau en carbure cémenté comprend des particules de carbure de tungstène ayant une grosseur de grain moyenne comprise entre 0,3 et 10 µm.

8. Outil rotatif composite (30, 110, 210) selon la revendication 1, caractérisé en ce qu'au moins l'un dudit premier matériau en carbure cémenté et dudit second matériau en carbure cémenté comprend des particules de carbure de tungstène ayant une grosseur de grain moyenne comprise entre 0,5 et 10 µm et l'autre dudit premier matériau en carbure cémenté et dudit second matériau en carbure cémenté comprend des particules de carbure de tungstène ayant une grosseur de grain moyenne comprise entre 0,3 et 1,5 µm.

9. Outil rotatif composite (30, 110, 210) selon la revendication 1, caractérisé en ce que l'outil rotatif composite (30, 110, 210) est sélectionné dans le groupe

constitué d'un foret, d'une fraise en bout et d'un taraud.

10. Outil rotatif composite (30, 110, 210) selon la revendication 2, **caractérisé en ce que** l'un dudit premier matériau en carbure cimenté et dudit second matériau en carbure cimenté comprend entre 1 et 10 pour cent en poids en plus dudit liant que l'autre dudit premier matériau en carbure cimenté et dudit second matériau en carbure cimenté.

11. Outil rotatif composite (30, 110, 210) selon la revendication 1, **caractérisé en ce qu'**au moins la dureté ou la résistance à l'usure dudit premier matériau en carbure cimenté à l'intérieur de l'âme (31) diffère de celle dudit second matériau en carbure cimenté à l'intérieur de ladite région extérieure (32).

12. Outil rotatif composite (30, 110, 210) selon la revendication 1, **caractérisé en ce que** ledit premier matériau en carbure cimenté comprend entre 2 et 6 pour cent en poids d'alliage de cobalt et ledit second matériau en carbure cimenté comprend entre 6 et 15 pour cent en poids d'alliage de cobalt.

13. Procédé pour produire un outil rotatif composite selon l'une quelconque des revendications 1 à 12, le procédé comprenant :

l'introduction d'une première poudre métallurgique dans une première région d'un vide d'un moule ;

l'introduction d'une seconde poudre métallurgique dans une seconde région du vide, la première poudre métallurgique différant de la seconde poudre métallurgique, ladite première poudre métallurgique étant sélectionnée pour donner, au moment de la consolidation, un premier matériau en carbure cimenté ayant un module d'élasticité compris entre 630 et 665 kN/mm<sup>2</sup> (entre 90x10<sup>6</sup> psi et 95x10<sup>6</sup> psi) et ladite seconde poudre métallurgique étant sélectionnée pour donner, au moment de la consolidation, un second matériau en carbure cimenté ayant un module d'élasticité compris entre 483 et 644 kN/mm<sup>2</sup> (entre 69x10<sup>6</sup> psi et 92x10<sup>6</sup> psi), ledit module d'élasticité du second matériau en carbure cimenté étant sélectionné pour être différent du et inférieur au module d'élasticité du premier matériau en carbure cimenté, la mise en contact d'au moins une partie de la première poudre métallurgique avec la seconde poudre métallurgique ;  
la compression du moule pour consolider la première poudre métallurgique et la seconde poudre métallurgique pour former un compact ;  
le frittage du compact par surpression ; et  
l'enlèvement du matériau du compact pour

donner au moins une arête tranchante orientée en hélice.

14. Procédé selon la revendication 13, **caractérisé en ce que** le moule est un moule sec en caoutchouc et, en outre, **caractérisé en ce que** la compression du moule comprend la compression isostatique du moule sec en caoutchouc pour former le compact.

15. Procédé selon la revendication 13, **caractérisé en ce que** l'enlèvement du matériau du compact comprend l'usinage du compact pour former au moins une cannelure orientée en hélice définissant au moins une arête tranchante orientée en hélice.

16. Procédé selon la revendication 13, comprenant, en outre :

la partition physique d'un vide du moule sec isostatique en caoutchouc pour former au moins la première région et la seconde région.

17. Procédé selon la revendication 16, **caractérisé en ce que** la partition physique du vide comprend l'insertion d'un manchon dans le vide pour diviser la première région et la seconde région.

18. Procédé selon la revendication 17, **caractérisé en ce que** la mise en contact d'au moins une partie de la première poudre métallurgique avec la seconde poudre métallurgique comprend l'enlèvement du manchon hors du vide après l'introduction de la première poudre métallurgique et de la seconde poudre métallurgique dans le moule.

19. Procédé selon la revendication 13, **caractérisé en ce que** le frittage du compact par surpression comprend le chauffage du compact à une température comprise entre 1350°C et 1500°C sous une pression de 2,07 à 13,79 N/mm<sup>2</sup> (300-2000 psi).

20. Procédé selon la revendication 13, **caractérisé en ce que** la mise en contact d'au moins une partie de la première poudre métallurgique avec la seconde poudre métallurgique comprend l'introduction de l'une de la première poudre métallurgique et la seconde poudre métallurgique dans le vide pour qu'elle soit en contact le long d'une interface avec l'autre de la première poudre métallurgique et la seconde poudre métallurgique.

21. Procédé selon la revendication 13, **caractérisé en ce que** la compression du moule comprend la compression isostatique du moule sous une pression de 34,5 à 345 N/mm<sup>2</sup> (5000 à 50000 psi).




FIG. 1(a)




FIG. 1(b)




FIG. 2(a)




FIG. 2(b)




FIG. 3(a)




FIG. 3(b)




FIG. 3(c)






FIG. 3(d)








FIG. 6




FIG. 7




FIG. 8




FIG. 9

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**